





## STEEL LADLE



## Applications

1	2	3	4	5
Pouring area	Impact area	Purging area	Sidewall lining	Slag area
Mortar for sealing nozzle	Impact tile	Precast well block for porous plug	Castable mix around bottom lining	Blocking mix on top lining
Slide gate sealing mortar	Blocking mix	Castable mix around well block	Ramming mix around bottom lining	Plastic mortar for blocking top lining
Precast well block	Hot repair castable mix	Ramming mix around well block	Back filling powder	Back filling powder
Castable mix around well block	Jointing cement	Mortar for sealing porous plug	Jointing cement	Jointing cement for safety bricks
Hot repair castable mixes		Hot repair castable mix	Mortar for repairing safety lining	



## Our Products

Area	Applications	Products
1) Pouring area	Mortar for sealing Intern nozzle	Refracol 29 DK,26 ASG DP
	Mastic cement for hot repair Intern nozzle	Refracol MI 4
	Mortars for slide gate assembly	Refracol 620,620 A, 286 AC
	Well block in tabular alumina precast mix	Refravibre 99
	Well block in Chrome oxyd-high alumina precast mix	Refravibre 940 A/3
	Well block in precast Spinel-alumina mix	Refravibre S390
	Tabular alumina castable mix around well block	Beton 9400
	Spinel - alumina self flowing mix around well block	Castalone S 712
	HA castable mix for well block hot repairing	Beton 940
2) Impact area	Spinel-alumina precast impact tile	In Refravibre S220, SM 692
	Self flowing castable mix for blocking impact tile	Castalone S712
	HA castable mix for well block hot repairing	Beton 940
	High alumina jointing mortar for HA and AMC bricks	Refracol 6, 6 A72, 6T
3) Purging area	Well block in high alumina or spinel-alumina precast mix	In Refravibre 99 / S390
	Well block in chrome oxyd - high alumina precast mix	In Refravibre 940 A/3
	High alumina castable mix for blocking well block	Beton 9400, 940
	Hot setting ramming mix for blocking well block	Refram 492
	HA heat setting mortar for sealing porous plug	Refracol 29 DK,26 ASG DP
	HA hot setting mortars for sealing porous plug	Refracol 620, 620 A
	HA castable mix for well block hot repairing	Beton 940
4) Sidewall lining	HA castable mixes for blocking bottom of wall lining	Beton 966, Rv 85 RX2
	Spinel - alumina castable mix for blocking bottom	Castalone S 712
	HA ramming mixes for blocking bottom of wall lining	PR 280, PR 288, PR 290
	Powder mix for filling back of working lining	Caloref 49 G
	High alumina jointing mortars for working lining	Refracol 6 A72, 6T
	High alumina jointing mortar for working lining	Refracol 790 SD
	Alumina air setting mortars for jointing safety bricks	Refracol 6, 8A, 6 A72
	Air setting cement for jointing insulating bricks	Refracol 12 A
	Plastic mortar for repairing safety lining	PR 116 CA
5) Slag aera	Castable mixes for blocking the top of working lining	Beton 955 D, 966
	Plastic mortar for blocking in the top the working lining	PR 116 CA
	Powder mix for Filling back working lining	Caloref 49 G
	Chromite air setting mortar for jointing safety bricks	Refracol 7
	Special blocks for protecting top metal plate	In FibroCeram

**REFRACOL DUPONT et Cie**

**B.P. 33 - F 59581 MARLY CEDEX**

Web : [www.refracol.com](http://www.refracol.com) - E-mail : [contact@refracol.com](mailto:contact@refracol.com)

**Tél. : +33 (0)3 27 46 37 76 - Fax : +33 (0)3 27 47 97 77**